

# specification



delfort

**Customer:** Europapier SK

**Date:**

**Grade:** OP Medical Print 45 gsm

**30.04.2020**

PARAMETER	UNIT	TARGET	MIN	MAX	STANDARD
Substance	g/m <sup>2</sup>	<b>45,0</b>	43,0	47,0	ISO 536
Thickness – 10 layers	µm	<b>56,0</b>	53,0	59,0	ISO 534
Tensile strength MD	kN/m	<b>2,4</b>	1,9	-	ISO 1924-2
Roughness T.V.	ml/min	-	-	300	ISO 8791-2
Brightness with UV	%	<b>95,0</b>	93,0	97,0	ISO 2470:2
Opacity	%	<b>86,0</b>	84,0	-	ISO 2471
Cobb <sub>60</sub> value	g/m <sup>2</sup>	<b>25,0</b>	-	32,0	ISO 535

Testing conditions: 50 % r.h., 23°C  
Tolerances (min/max) are based on individual values  
T.V. – typical value

Roman Kotrlý  
Customer Service Thin Printing Paper

