

### Technical specifications

Property	Test Method	Unit	Tolerance	100	120	140
Substance	ISO 536 TAPPI T410	g/m <sup>2</sup>	±4%	100	120	140
Thickness	ISO 534 TAPPI T411	µm	±4%	118	140	158
Bulk	ISO 534 TAPPI T411	cm <sup>3</sup> /g	-	1.18	1.17	1.13
Opacity	ISO 2471 TAPPI T519	%	-2.0	94.5	96.0	97.5
Whiteness D65/10°	ISO 11475	CIE	±3	121	121	121
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	6	6	6
Parker roughness	ISO 8791-4 TAPPI T555	mm	≤1,30*STD	5.5	5.5	5.5
Relative humidity	TAPPI T502	%	±7	50	50	50

Values are subject to change without notice.

Last update: 21/03/2022